

Lithium-Manganese button cell (Data Sheet)

BRAND	unique <sup>®</sup> energy
PRODUCT	3.0V LITHIUM-MANGANESE BUTTON CELL
MODEL	CR2430
PREPARED BY	
APPROVED BY	
DATE	JANUARY. 18, 2010

### 1. SCOPE

This specification applies to the following 3.0v lithium button cell CR2430 made by Unique Energy.

## 2. RATINGS

TABLE :

ITEM		UNIT	SPECIFICATIONS	CONDITIONS	
Nominal voltage		V	3.0	Standard discharge	
Nominal capacity		mAh	270	Standard discharge with load 15kΩ	
Off-load voltage		V	≥3.2		
Storage temperature		°C	0~35		
Standard weight		g	4.3	Unit cell	
Service output	Initial	Standard	684 h	Continuous discharge with load 7.5kΩ, till 2.0v end-voltage at 20~25°C	
	After 12 months storage	Standard	643 h		

#### TABLE:

ITEM	CONDITIONS	CHARACTERISTICS	
Thermal durability	Kept for 20 days at $60^{\circ}C\pm3^{\circ}C$ , then continuously discharge with 7.5k $\Omega$ load till 2.0v end-voltage	Standard	643 h
Self-discharge rate	Stored for 12 months at normal temperature and humidity	≪5%	

## 3. PERFORMANCE AND TEST METHODS

Unless otherwise stated, all the testing is carried out under the condition: environmental temperature,  $20^{\circ}C \sim 25^{\circ}C$ ; environmental humidity,  $50\pm10\%$ . Please refer to Table


# 4. SUGGESTIONS AND CAUTIONS

- 4.1 Install batteries correctly.
- 4.2 Ensure the contact points to be clean and conductive.
- 4.3 Do not mix different types, different brands batteries to serve together.
- 4.4 Do not heat, recharge the batteries.
- 4.5 Do not dispose of the batteries in fire.
- 4.6 Keep away from the small children, if swallowed promptly see doctor.
- 4.7 Pay attention to the producing date.

No	ITEM	TEST METHODS	STANDARED		
1 Dimen	Dimensions	Using vernier caliper (accuracy≥0.02) while avoiding short-circuit	Diameter	24.5(-0.20)mm	
	Dimensions		Height	3.0(-0.20) mm	
2	Off-load voltage	Using multimeter (accuracy $\ge 0.25\%$ ) internal resistance $\ge 1M\Omega$	≥3.2v		
3	Appearance	Eyeballing	Bright, clean, no rust, no leakage, and no flaw		
4	Capacity	Continuously discharge for 8 hours with load 7.5kΩ, temperature at 20~25°C, humidity at 50±10% till 2.0v end-voltage (for fresh battery only: within 3 months)	≥684 h		
5	Vibration test	Put battery on the platform of the vibrations machine, start the machine and adjust the frequency form 10 times per minute to 15 times per minute. Keep it running for an hour.	Characteristics keep stability		
6	Leakage at high temperature	Stored under temperature (60°C) for 3 days	No leakage allowed		
7	Over discharge Test	After 2.0v end-voltage, continuously discharged for 5 hours	No leakage allowed		

#### TABLE:

# 5. CUTAWAY DIAGRAM OF 3.0V LITHIUM MANGANESE DIOXIDE BUTTON CELL



- 1、Cathode Shell
- 2. Cathode collector net
- 3、Cathode (slice of lithium)
- 7. Anode collector net

- 5, Gasket
- 6, Anode(MnO<sub>2</sub>)

8, Anode shell

4、Septum